Refine Search

Search Results -

Term	Documents
(7 AND 1).PGPB,USPT,DWPI.	1
(L1 AND L7).PGPB,USPT,DWPI.	1

Database:
US Pre-Grant Publication Full-Text Database
US Patents Full-Text Database
US OCR Full-Text Database
EPO Abstracts Database
JPO Abstracts Database
Derwent World Patents Index
IBM Technical Disclosure Bulletins

Search: L8

Refine Search | Recall Text | Clear | Interrupt

Search History

DATE: Friday, February 13, 2004 Printable Copy Create Case

Set Name side by side	Query	Hit Count	Set Name result set
DB=PGPB,USPT,DWPI; PLUR=YES; OP=ADJ			
L8	L1 AND L7	1	L8
L7	L3 AND L4 AND L5 AND L6	17	L7
L6	COATING SAME (POLYVINYL CHLORIDE OR POLY VINYL CHLORIDE OR POLYURETHANE)	51756	L6
L5	((NYLON 6 OR NYLON 66 OR (NYLON 6 OR NYLON 66) OR BLENDS))	228862	L5
L4	POINTBONDED OR POINT BONDED OR POINT-BONDED	1015	L4
L3	NONWOVEN OR NON-WOVEN OR UNWOVEN OR UN-WOVEN	101499	L3
L2	BASE SAME FABRIC	35244	L2
L1	(FOOTWEAR OR FOOT WEAR OR FOOT-WEAR) SAME UPPER	3743	L1

END OF SEARCH HISTORY

h e b b cg b e e ch

Connecting via Winsock to STN

Welcome to STN International! Enter x:x

LOGINID:sssptau155jjg

PASSWORD:
TERMINAL (ENTER 1, 2, 3, OR ?):2

* * * * * * * * * * Welcome to STN International * * * * * * * * * *

NEWS 1		Web Page URLs for STN Seminar Schedule - N. America
NEWS 2		"Ask CAS" for self-help around the clock
NEWS 3	SEP 09	CA/CAplus records now contain indexing from 1907 to the present
NEWS 4	DEC 08	INPADOC: Legal Status data reloaded
NEWS 5	SEP 29	DISSABS now available on STN
NEWS 6	OCT 10	PCTFULL: Two new display fields added
NEWS 7	OCT 21	BIOSIS file reloaded and enhanced
NEWS 8	OCT 28	BIOSIS file segment of TOXCENTER reloaded and enhanced
NEWS 9	NOV 24	MSDS-CCOHS file reloaded
NEWS 10	DEC 08	CABA reloaded with left truncation
NEWS 11	DEC 08	IMS file names changed
NEWS 12	DEC 09	Experimental property data collected by CAS now available in REGISTRY
NEWS 13	DEC 09	STN Entry Date available for display in REGISTRY and CA/CAplus
NEWS 14	DEC 17	DGENE: Two new display fields added
NEWS 15	DEC 18	BIOTECHNO no longer updated
NEWS 16	DEC 19	CROPU no longer updated; subscriber discount no longer available
NEWS 17	DEC 22	Additional INPI reactions and pre-1907 documents added to CAS databases
NEWS 18	DEC 22	IFIPAT/IFIUDB/IFICDB reloaded with new data and search fields
NEWS 19	DEC 22	ABI-INFORM now available on STN
NEWS 20	JAN 27	Source of Registration (SR) information in REGISTRY updated and searchable
NEWS 21	JAN 27	A new search aid, the Company Name Thesaurus, available in CA/CAplus
NEWS 22	FEB 05	German (DE) application and patent publication number format changes

NEWS EXPRESS	DECEMBER 28 CURRENT WINDOWS VERSION IS V7.00, CURRENT MACINTOSH VERSION IS V6.0b(ENG) AND V6.0Jb(JP), AND CURRENT DISCOVER FILE IS DATED 23 SEPTEMBER 2003
NEWS HOURS	STN Operating Hours Plus Help Desk Availability
NEWS INTER	General Internet Information
NEWS LOGIN	Welcome Banner and News Items
NEWS PHONE	Direct Dial and Telecommunication Network Access to STN
NEWS WWW	CAS World Wide Web Site (general information)

Enter NEWS followed by the item number or name to see news on that specific topic.

```
  * * * * * * * * * * * * * * STN  Columbus  * * * * * * * * * * * * * * *

FILE 'HOME' ENTERED AT 08:52:50 ON 13 FEB 2004

=> S (footwear or foot-wear or foot wear)(1)upper
THIS COMMAND NOT AVAILABLE IN THE CURRENT FILE
Some commands only work in certain files.  For example, the EXPAND
command can only be used to look at the index in a file which has an
index.  Enter "HELP COMMANDS" at an arrow prompt (=>) for a list of
commands which can be used in this file.

=> file caplus
COST IN U.S. DOLLARS                                  SINCE FILE      TOTAL
                                                         ENTRY    SESSION
FULL ESTIMATED COST                                       0.84       0.84

FILE 'CAPLUS' ENTERED AT 08:55:02 ON 13 FEB 2004
USE IS SUBJECT TO THE TERMS OF YOUR STN CUSTOMER AGREEMENT.
PLEASE SEE "HELP USAGETERMS" FOR DETAILS.
COPYRIGHT (C) 2004 AMERICAN CHEMICAL SOCIETY (ACS)


Copyright of the articles to which records in this database refer is
held by the publishers listed in the PUBLISHER (PB) field (available
for records published or updated in Chemical Abstracts after December
26, 1996), unless otherwise indicated in the original publications.
The CA Lexicon is the copyrighted intellectual property of the
American Chemical Society and is provided to assist you in searching
databases on STN.  Any dissemination, distribution, copying, or storing
of this information, without the prior written consent of CAS, is
strictly prohibited.

FILE COVERS 1907 - 13 Feb 2004  VOL 140 ISS 7
FILE LAST UPDATED: 11 Feb 2004  (20040211/ED)

  This file contains CAS Registry Numbers for easy and accurate
  substance identification.


=> s (footwear or foot wear or foot-wear)(1)upper
          2507 FOOTWEAR
             2 FOOTWEARS
          2508 FOOTWEAR
                 (FOOTWEAR OR FOOTWEARS)
         15736 FOOT
           502 FOOTS
          3964 FEET
             3 FEETS
         19620 FOOT
                 (FOOT OR FOOTS OR FEET OR FEETS)
        104604 WEAR
          1416 WEARS
        105594 WEAR
                 (WEAR OR WEARS)
            36 FOOT WEAR
                 (FOOT(W)WEAR)
         15736 FOOT
           502 FOOTS
          3964 FEET
             3 FEETS
         19620 FOOT
                 (FOOT OR FOOTS OR FEET OR FEETS)
        104604 WEAR
          1416 WEARS
```

```
        105594 WEAR
                 (WEAR OR WEARS)
            36 FOOT-WEAR
                 (FOOT(W)WEAR)
        235258 UPPER
          1177 UPPERS
        235893 UPPER
                 (UPPER OR UPPERS)
L1         283 (FOOTWEAR OR FOOT WEAR OR FOOT-WEAR)(L)UPPER

=> s nonwoven or non-woven or unwoven or un-woven
         28304 NONWOVEN
          2713 NONWOVENS
         28547 NONWOVEN
                 (NONWOVEN OR NONWOVENS)
        636600 NON
            32 NONS
        636625 NON
                 (NON OR NONS)
         19712 WOVEN
           101 WOVENS
         19788 WOVEN
                 (WOVEN OR WOVENS)
          2302 NON-WOVEN
                 (NON(W)WOVEN)
          1002 UNWOVEN
         50955 UN
          1810 UNS
         52759 UN
                 (UN OR UNS)
         19712 WOVEN
           101 WOVENS
         19788 WOVEN
                 (WOVEN OR WOVENS)
            10 UN-WOVEN
                 (UN(W)WOVEN)
L2       30840 NONWOVEN OR NON-WOVEN OR UNWOVEN OR UN-WOVEN

=> s coating(1)(polyurethane or polyvinyl chloride or poly vinyl chloride)
        652044 COATING
        329667 COATINGS
        707682 COATING
                 (COATING OR COATINGS)
        104940 POLYURETHANE
         70217 POLYURETHANES
        122641 POLYURETHANE
                 (POLYURETHANE OR POLYURETHANES)
         75164 POLYVINYL
           162 POLYVINYLS
         75280 POLYVINYL
                 (POLYVINYL OR POLYVINYLS)
        977136 CHLORIDE
        148749 CHLORIDES
       1044853 CHLORIDE
                 (CHLORIDE OR CHLORIDES)
         13814 POLYVINYL CHLORIDE
                 (POLYVINYL(W)CHLORIDE)
        598742 POLY
        372919 VINYL
           541 VINYLS
        373069 VINYL
                 (VINYL OR VINYLS)
        977136 CHLORIDE
        148749 CHLORIDES
```

```
       1044853 CHLORIDE
                 (CHLORIDE OR CHLORIDES)
         41268 POLY VINYL CHLORIDE
                 (POLY(W)VINYL(W)CHLORIDE)
L3       32855 COATING(L)(POLYURETHANE OR POLYVINYL CHLORIDE OR POLY VINYL
               CHLORIDE)

=> s laminate
         79806 LAMINATE
         59081 LAMINATES
L4       98421 LAMINATE
                 (LAMINATE OR LAMINATES)

=> d his

     (FILE 'HOME' ENTERED AT 08:52:50 ON 13 FEB 2004)

     FILE 'CAPLUS' ENTERED AT 08:55:02 ON 13 FEB 2004
L1           283 S (FOOTWEAR OR FOOT WEAR OR FOOT-WEAR)(L)UPPER
L2         30840 S NONWOVEN OR NON-WOVEN OR UNWOVEN OR UN-WOVEN
L3         32855 S COATING(L)(POLYURETHANE OR POLYVINYL CHLORIDE OR POLY VINYL C
L4         98421 S LAMINATE

=> s l2 and l3 and l4
L5           151 L2 AND L3 AND L4

=> s l1 and l5
L6             2 L1 AND L5

=> d l6 1-2 bib,abs

L6   ANSWER 1 OF 2  CAPLUS  COPYRIGHT 2004 ACS on STN
AN   2002:31947  CAPLUS
DN   136:87203
TI   Two-in-one shoe components
IN   O'Hare, Kieran
PA   UK
SO   U.S. Pat. Appl. Publ., 3 pp.
     CODEN: USXXCO
DT   Patent
LA   English
FAN.CNT 1
     PATENT NO.         KIND  DATE           APPLICATION NO.  DATE
     ---------------    ----  --------       ---------------  --------
PI   US 2002004345       A1   20020110       US 2001-681973   20010702
     WO 2002004740       A2   20020117       WO 2001-US21252  20010705
     WO 2002004740       A3   20020613
         W:  AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN,
             CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR,
             HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT,
             LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU,
             SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU,
             ZA, ZW, AM, AZ, BY, KG, KZ, MD, RU, TJ, TM
         RW: GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW, AT, BE, CH, CY,
             DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR, BF,
             BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG
     AU 2001073182       A5   20020121       AU 2001-73182    20010705
     EP 1299593          A2   20030409       EP 2001-952429   20010705
         R:  AT, BE, CH, DE, DK, ES, FR, GB, GR, IT, LI, LU, NL, SE, MC, PT,
             IE, SI, LT, LV, FI, RO, MK, CY, AL, TR
     BR 2001012316       A    20030610       BR 2001-12316    20010705
PRAI US 2000-216098P     P    20000706
     US 2001-681973      A    20010702
     WO 2001-US21252     W    20010705
```

AB A **footwear upper** is made from a **laminate** of a thermally point-bonded **nonwoven** base fabric and a **coating** of **polyurethane** or **polyvinyl chloride** on ≥1 surface of the base fabric, wherein the **upper** functions addnl. as a lining for the **footwear**.

L6 ANSWER 2 OF 2 CAPLUS COPYRIGHT 2004 ACS on STN
AN 1983:596322 CAPLUS
DN 99:196322
TI Flexible, flat, **laminates** with a fiber base
IN Foltan, Ivan; Benkovic, Ivan; Schaffer, Ludovit; Duracka, Miroslav; Kurtan, Geza
PA Czech.
SO Czech., 3 pp.
CODEN: CZXXA9
DT Patent
LA Slovak
FAN.CNT 1

PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI CS 197673	B	19800530	CS 1977-6899	19771024
PRAI CS 1977-6899		19771024		

AB Material for **footwear uppers** and linings with a brilliant multicolor pattern is obtained from a fibrous layer, containing 60-70% polyester fibers and bonded with 30-60% latex of nitrile rubber, polyacrylate, or **polyurethane**, which was patterned by sublimation printing and **coating** with an 0.1-0.7-mm transparent layer of PVC [9002-86-2], nitrile rubber, polyamide, or a **polyurethane**-PVC mixture Thus, a needle-punched **nonwoven** fabric containing polyester 70, polypropylene 10, and viscose fibers 20% (300 g/m2) was impregnated with 50% nitrile rubber, split, ground on one side, sublimation-printed at 190-210° from a paper matrix, coated with a transparent PV paste, and gelled at 120 and 170°.

=> d his

(FILE 'HOME' ENTERED AT 08:52:50 ON 13 FEB 2004)

FILE 'CAPLUS' ENTERED AT 08:55:02 ON 13 FEB 2004
L1 283 S (FOOTWEAR OR FOOT WEAR OR FOOT-WEAR)(L)UPPER
L2 30840 S NONWOVEN OR NON-WOVEN OR UNWOVEN OR UN-WOVEN
L3 32855 S COATING(L)(POLYURETHANE OR POLYVINYL CHLORIDE OR POLY VINYL C
L4 98421 S LAMINATE
L5 151 S L2 AND L3 AND L4
L6 2 S L1 AND L5

=> s nylon 6 or nylon 66 or blends
73462 NYLON
1985 NYLONS
73832 NYLON
(NYLON OR NYLONS)
3378729 6
25097 NYLON 6
(NYLON(W)6)
73462 NYLON
1985 NYLONS
73832 NYLON
(NYLON OR NYLONS)
183465 66
12460 NYLON 66
(NYLON(W)66)
132810 BLENDS
L7 159317 NYLON 6 OR NYLON 66 OR BLENDS

```
=> d his

     (FILE 'HOME' ENTERED AT 08:52:50 ON 13 FEB 2004)

     FILE 'CAPLUS' ENTERED AT 08:55:02 ON 13 FEB 2004
L1           283 S (FOOTWEAR OR FOOT WEAR OR FOOT-WEAR)(L)UPPER
L2         30840 S NONWOVEN OR NON-WOVEN OR UNWOVEN OR UN-WOVEN
L3         32855 S COATING(L)(POLYURETHANE OR POLYVINYL CHLORIDE OR POLY VINYL C
L4         98421 S LAMINATE
L5           151 S L2 AND L3 AND L4
L6             2 S L1 AND L5
L7        159317 S NYLON 6 OR NYLON 66 OR BLENDS

=> s l2 and l7 and l4
L8           590 L2 AND L7 AND L4

=> s l1 and l8
L9             0 L1 AND L8

=> s l2 and l3 and l7
L10          145 L2 AND L3 AND L7

=> s l10 and l1
L11            0 L10 AND L1

=> s footwear upper
            2507 FOOTWEAR
               2 FOOTWEARS
            2508 FOOTWEAR
                 (FOOTWEAR OR FOOTWEARS)
          235258 UPPER
            1177 UPPERS
          235893 UPPER
                 (UPPER OR UPPERS)
L12          143 FOOTWEAR UPPER
                 (FOOTWEAR(W)UPPER)

=> s l10 and l12
L13            0 L10 AND L12

=> s lining
           39031 LINING
           23943 LININGS
L14        46715 LINING
                 (LINING OR LININGS)

=> d his

     (FILE 'HOME' ENTERED AT 08:52:50 ON 13 FEB 2004)

     FILE 'CAPLUS' ENTERED AT 08:55:02 ON 13 FEB 2004
L1           283 S (FOOTWEAR OR FOOT WEAR OR FOOT-WEAR)(L)UPPER
L2         30840 S NONWOVEN OR NON-WOVEN OR UNWOVEN OR UN-WOVEN
L3         32855 S COATING(L)(POLYURETHANE OR POLYVINYL CHLORIDE OR POLY VINYL C
L4         98421 S LAMINATE
L5           151 S L2 AND L3 AND L4
L6             2 S L1 AND L5
L7        159317 S NYLON 6 OR NYLON 66 OR BLENDS
L8           590 S L2 AND L7 AND L4
L9             0 S L1 AND L8
L10          145 S L2 AND L3 AND L7
L11            0 S L10 AND L1
L12          143 S FOOTWEAR UPPER
```

L13 0 S L10 AND L12
L14 46715 S LINING

=> s l10 and l14
L15 5 L10 AND L14

=> d l15 1-5 bib, abs

L15 ANSWER 1 OF 5 CAPLUS COPYRIGHT 2004 ACS on STN
AN 2003:653276 CAPLUS
DN 139:198762
TI Physical treatment of **nonwoven** fabrics to reduce pilling
IN Kalbe, Michael; Marg, Uwe
PA Carl Freudenberg K.-G., Germany
SO Eur. Pat. Appl., 10 pp.
CODEN: EPXXDW
DT Patent
LA German
FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	EP 1336682	A2	20030820	EP 2003-3393	20030214
	EP 1336682	A3	20040102		
	R: AT, BE, CH, DE, DK, ES, FR, GB, GR, IT, LI, LU, NL, SE, MC, PT, IE, SI, LT, LV, FI, RO, MK, CY, AL, TR, BG, CZ, EE, HU, SK				
	US 2003221301	A1	20031204	US 2003-368241	20030218
PRAI	DE 2002-10206840	A	20020218		

AB A method for avoiding or at least reducing pilling of **nonwoven** fabrics (fleece) made from unsplit and/or at least partially split microfibers and/or microfilaments of synthetic polymers and comprising at least one polyester component, at least one polyamide component and, optionally, at least one **polyurethane** component, the **nonwoven** fabrics being treated at least once by a phys. method. Phys. treatment can be thermal treatment, treatment with flame, dry hot air, water steam, calendering, **coating**, and screen printing. The treated **nonwovens** can be used for production of textile coverings, banners, luggage container **linings**, and inner components of vehicles. Thus, a **nonwoven** fabric having surface weight of 115 g/m2 and comprising partially (85%) split microfilaments of polyamide 66 (30) and poly(ethylene terephthalate) (70%) was dyed using a dispersion dye and treated with flame of minimal intensity.

L15 ANSWER 2 OF 5 CAPLUS COPYRIGHT 2004 ACS on STN
AN 1997:510077 CAPLUS
DN 127:122935
TI Bondable interlinings with improved bonding strength durability and garments from them
IN Nakamura, Tatsuro; Yokoyama, Takahiro
PA Japan Vilene Co., Ltd., Japan
SO Jpn. Kokai Tokkyo Koho, 6 pp.
CODEN: JKXXAF
DT Patent
LA Japanese
FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	JP 09158055	A2	19970617	JP 1995-336024	19951129
	JP 3184442	B2	20010709		
PRAI	JP 1995-336024		19951129		

AB The interlinings are prepared by **coating** fibrous sheets with compns. comprising adhesive polymers and 1-15% **polyurethanes** containing blocked isocyanate groups. A **nonwoven** fabric of nylon fibers was treated with a silicone waterproofing agent, screen printed with an aqueous paste containing 26.2 parts polyamide and 2.7 parts NaHSO3-blocked

adipic acid-butylene glycol-hexamethylene diisocyanate block copolymer, and heat-treated 60 s at 100° to give a bondable interlining. The interlining and a wool fabric were together pressed for 10 s at 130° to give a bonded fabric with layer bonding strength ≈0.7 kg/5 cm width and good bonding strength retention after 30 s under steam at 5 kg/cm2.

L15 ANSWER 3 OF 5 CAPLUS COPYRIGHT 2004 ACS on STN
AN 1991:609719 CAPLUS
DN 115:209719
TI Manufacture of **linings** for sound-insulating floor materials
IN Yagi, Keisuke
PA Sumitomo Bakelite Co., Ltd., Japan
SO Jpn. Kokai Tokkyo Koho, 6 pp.
CODEN: JKXXAF
DT Patent
LA Japanese
FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	JP 03051379	A2	19910305	JP 1989-183722	19890718
	JP 06065788	B4	19940824		
PRAI	JP 1989-183722		19890718		

AB The title process involves coating stiff polyester fibers (2000-5000 denier) with a vinyl chloride (I) type resin containing 0-50 parts plasticizers and 100 parts reaction products (urethane ratio 30-60%) of isocyanates and polyol-containing I polymers, subjecting the coating to a shrinkage treatment, and forming mat-like materials. Kneading Dominus K550F 100, Ba-Zn stabilizer 3, and DOP 10 parts, melt coating the pellets onto stiff polyester fibers (3000 denier), subjecting to a shrinking treatment, forming a mat, sandwiching with **nonwoven** cloths, and lapping the sandwiched mat (8 mm) with a 2-mm rubber mat, a 2-mm plywood, a 2-mm paper cushion, and a 10-mm floor panel gave a 24-mm floor material (urethane content 60%) with sound insulation grade (Japan Construction Society) L-40.

L15 ANSWER 4 OF 5 CAPLUS COPYRIGHT 2004 ACS on STN
AN 1991:537772 CAPLUS
DN 115:137772
TI Manufacture of bending- and water-resistant sheets with sponge structure
IN Tanaka, Jiro; Taniguchi, Toshiro
PA Kuraray Co., Ltd., Japan
SO Jpn. Kokai Tokkyo Koho, 6 pp.
CODEN: JKXXAF
DT Patent
LA Japanese
FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	JP 02264082	A2	19901026	JP 1989-82102	19890331
	JP 2801253	B2	19980921		
PRAI	JP 1989-82102		19890331		

AB The title process comprises impregnating and/or **coating** onto a fabric substrate a composition of **polyurethane** elastomer, a polyether-modified silicone oil, a polyoxyethylene-polyoxypropylene block copolymer, and a solvent and coagulating in a nonsolvent, where the **polyurethane** elastomer is the reaction product of an organic diisocyanate, a chain extender, and a polyester diol prepared using mainly 1.9-nonanediol (I) and/or 2-methyl-1,8-octanediol (II) as the diol component. Reacting 1:6:5 mol I-II-adipic acid copolymer diol, 4,4'-MDI, and 1,4-butanediol, diluting the elastomer with DMF to 13% solution, and mixing with 60% (based on the elastomer) 1/2 Crisvon Asistor SD7 and Crisvon Asistor SD14 gave an elastomer composition Soaking a 60/40 **nylon** 6-polyethylene **nonwoven** cloth in the composition, coagulating

the **nonwoven** cloth in 30% aqueous DMF, removing the polyethylene component by treating in hot PhMe, drying, puffing, and dyeing gave a suedelike sheet with uniform sponge structure.

L15 ANSWER 5 OF 5 CAPLUS COPYRIGHT 2004 ACS on STN
AN 1973:137526 CAPLUS
DN 78:137526
TI Production of leather substitutes for shoes by lamination
AU Szumarowska, Bogumila; Zelenski, Piotr; Supera, Anna
CS Zakl. Badan Chem., Inst. Przem. Skorzanego, Lodz, Pol.
SO Prace Instytutu Przemyslu Skorzanego (1972), 16, 227-39
CODEN: PIPSAC; ISSN: 0509-6790
DT Journal
LA Polish
AB Exptl. leather substitutes were made by **coating** **nonwoven** fabrics or (for comparison) cotton with microporous **polyurethane** film. The **nonwoven** fabrics consisted of 2 layers: porous inner **lining** of fine fibers (polyester, casein-based, collagen, polypropylene, polyamide, or their **blends**) bonded with a flexible resin and a supporting middle layer made of coarse, strong fiber or cotton. None of the laminates tested had sufficient flexural strength or satisfactory appearance, but the moisture sorption-desorption characteristics surpassed Corfam.